

【酸化チタン粒子径】

検査期間：京都大学

ナノゾーンソリューションに配合の酸化チタンが2-3nm（ナノメートル）であるというエビデンス



Division of Food Science and Biotechnology,
Graduate School of Agriculture, Kyoto University,
Sakyo-ku, Kyoto 606-8502, Japan




Table 1. Particle-size of sample 1

Peak No.	Mean diameter [nm]	SD [nm]
1	3.3	0.3
2	11.2	2.3
3	157.9	26.1

Fig. 1. Frequent and cumulative distributions of particle size in sample 1.




Table 2. Particle-size of sample 2

Measurement	Peak No.	Mean diameter [nm]	SD [nm]
1st	1	2.4	0.4
	2	31.2	10.6
2nd	1	17	3.7
	2	79.7	12.6

Fig. 2. Frequent and cumulative distributions of particle size in sample 2. The distributions were measured twice under the same conditions after 1.5-h interval.




Table 1. Particle-size of sample 1

Peak No.	Mean diameter [nm]	SD [nm]
1	3.3	0.3
2	11.2	2.3
3	157.9	26.1

Fig. 1. Frequent and cumulative distributions of particle size in sample 1.




Table 2. Particle-size of sample 2

Measurement	Peak No.	Mean diameter [nm]	SD [nm]
1st	1	2.4	0.4
	2	31.2	10.6
2nd	1	17	3.7
	2	79.7	12.6

Fig. 2. Frequent and cumulative distributions of particle size in sample 2. The distributions were measured twice under the same conditions after 1.5-h interval.